

For more information and technical assistance contact ConocoPhillips COPYLENE™ Polypropylene at www.COPYLENE.com.

COPYLENE™ CH016

Polypropylene, Homopolymer

Applications

- Bags & Pouches
- Raffia/Tapes/Strapping
- Peelable Film
- Film Wrap
- Food Packaging Film
- Lamination Film
- Twist Wrap Film
- Surface Protection Film
- Barrier Film

Product Description

- COPYLENE™ CH016 is a polypropylene homopolymer resin designed for BOPP (biaxially oriented polypropylene) film extrusion applications.

Product Properties

Typical Properties	Method	Value Unit
Physical		
Melt Flow Rate (230°C/2.16kg)	ASTM D 1238	1.6 g/10 min
Density – Specific Gravity	ASTM D 792	0.902 sp gr
Mechanical		
Tensile Strength @ Yield (2 in/min) (50 mm/min)	ASTM D 638	4800 psi 33.1 MPa
Flexural Modulus (0.05 in/min, 1% Secant, Procedure A) (1 mm/min, 1% Secant, Procedure A)	ASTM D 790	200000 psi 1378 MPa
Tensile Elongation @Yld	ASTM D 638	12%
Impact		
Notched izod impact (73 °F, Method A) (23 °C, Method A)	ASTM D 256	1.0 ft-lb/in 53.0 J/m
Thermal		
DTUL @66psi – Unannealed	ASTM D 648	92 °C

For regulatory compliance information, see COPYLENE™ CH016 Product Stewardship Information Sheet. MSDS available upon request, or on our Web site at www.COPYLENE.com. The product specifications are nominal properties and do not reflect normal testing variance and should not be used for specification purposes.

Revision Date June 2011



Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user's specific application. ConocoPhillips Company does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, express or implied, or allegedly arising from any usage of any trade or from any course of dealing in connection with the use of the information contained herein or the product itself. The user expressly assumes all risk and liability, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Further, information contained herein is given without reverence to any intellectual property issues, as well as federal, state or local laws which may be encountered in the use thereof. Such questions should be investigated by the user.

COPYLENE™ is a trademark of ConocoPhillips Co. or one of its subsidiaries.