

For more information and technical assistance contact ConocoPhillips COPYLENE™ Polypropylene at www.COPYLENE.com.

COPYLENE™ CR350LN

Random Copolymer

Applications:

- Containers
- Closures
- Housewares

Product Description

- COPYLENE™ CR350LN is a high flow random copolymer nucleated and with antistat for good mold release in injection molding applications.

Product Properties

Typical Properties	Method	Value Unit
Physical		
Melt Flow Rate (230°C/2.16kg)	ASTM D 1238	35 g/10 min
Density – Specific Gravity	ASTM D 792	0.902 sp gr
Mechanical		
Tensile Strength @ Yield (2 in/min) (50 mm/min)	ASTM D 638	4000 psi 27.6 MPa
Flexural Modulus (0.05 in/min, 1% Secant, Procedure A) (1 mm/min, 1% Secant, Procedure A)	ASTM D 790	160000 psi 1310 MPa
Tensile Elongation @Yld	ASTM D 638	12.5%
Impact		
Notched izod impact (73 °F, Method A) (23 °C, Method A)	ASTM D 256	1.1 ft-lb/in 58.3 J/m
Thermal		
DTUL @66psi – Unannealed	ASTM D 648	88 °C

For regulatory compliance information, see COPYLENE™ CR350LN Product Stewardship Information Sheet. MSDS available upon request, or on our Web site at www.COPYLENE.com. The product specifications are nominal properties and do not reflect normal testing variance and should not be used for specification purposes.

Revision Date February 2012



Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user's specific application. ConocoPhillips Company does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, express or implied, or allegedly arising from any usage of any trade or from any course of dealing in connection with the use of the information contained herein or the product itself. The user expressly assumes all risk and liability, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Further, information contained herein is given without reverence to any intellectual property issues, as well as federal, state or local laws which may be encountered in the use thereof. Such questions should be investigated by the user.

COPYLENE™ is a trademark of ConocoPhillips Co. or one of its subsidiaries.