

For more information and technical assistance contact Phillips 66 COPYLENE® Polypropylene at [www.COPYLENE.com](http://www.COPYLENE.com).

## COPYLENE® CM017L

Developmental Impact Copolymer

### Applications:

- Corrugated sheet
- Sheet extrusion

### Product Description

- COPYLENE® CM017L is a high impact copolymer with an excellent balance of stiffness and impact performance for profile extrusion.

### Product Properties

Typical Properties	Method	Value Unit
<b>Physical</b>		
Melt Flow Rate (230°C/2.16kg)	ASTM D 1238	1.8 g/10 min
Density – Specific Gravity	ASTM D 792	0.9 sp gr
<b>Mechanical</b>		
Tensile Strength @ Yield (2 in/min) (50 mm/min)	ASTM D 638	3,670 psi 25.3 MPa
Flexural Modulus (0.05 in/min, 1% Secant, Procedure A) (1 mm/min, 1% Secant, Procedure A)	ASTM D 790	165,000 psi 1138 MPa
Tensile Elongation @Yld	ASTM D 638	12.7%
<b>Impact</b>		
Notched izod impact (73 °F, Method A) (23 °C, Method A)	ASTM D 256	7.7
<b>Thermal</b>		
DTUL @66psi – Unannealed	ASTM D 648	80 °C

For regulatory compliance information, see COPYLENE® CM017L Product Stewardship Information Sheet. SDS available upon request, or on our Web site at [www.COPYLENE.com](http://www.COPYLENE.com). The product specifications are nominal properties and do not reflect normal testing variance and should not be used for specification purposes.

Revision Date June 2020



Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited, and the information is applicable to the user's specific application. Phillips 66 Company does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, express or implied, or allegedly arising from any usage of any trade or from any course of dealing in connection with the use of the information contained herein or the product itself. The user expressly assumes all risk and liability, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Further, information contained herein is given without reverence to any intellectual property issues, as well as federal, state or local laws which may be encountered in the use thereof. Such questions should be investigated by the user.

PHILLIPS 66®, PHILLIPS 66® Shield, COPYLENE® and other trademarks displayed herein are registered trademarks of Phillips 66 Company or one of its subsidiaries.