

For more information and technical assistance contact Phillips 66 COPYLENE® Polypropylene at [www.COPYLENE.com](http://www.COPYLENE.com).

## COPYLENE® CM350LN

Polypropylene, Impact Copolymer

### Applications:

- Caps & Closures
- Opaque Containers

### Product Description

- COPYLENE® CM350LN is a high melt flow, controlled rheology, medium impact polypropylene copolymer resin designed for injection molding applications requiring a good balance of stiffness, impact, resistance and processability.

### Product Properties

Typical Properties	Method	Value Unit
<b>Physical</b>		
Melt Flow Rate (230 °C/2.16kg)	ASTM D 1238	38.0 g/ 10 min
Density – Specific Gravity	ASTM D 792	0.902 sp. gr
<b>Mechanical</b>		
Tensile Strength @ Yield (2 in/min) (50 mm/min)	ASTM D 638	3,300 psi 22.8 MPa
Flexural Modulus (0.05 in/min, 1% Secant, Procedure A) (1 mm/min, 1% Secant, Procedure A)	ASTM D 790	170,000 psi 1,170 MPa
Tensile Elongation @Yld	ASTM D 638	6%
<b>Impact</b>		
Notched Izod impact (73 °F, Method A) (23 °C, Method A)	ASTM D 256	2.3 ft-lb/in 123 J/m
<b>Thermal</b>		
DTUL @66psi – Unannealed	ASTM D 648	102 °C

For regulatory compliance information, see COPYLENE® CM350LN Product Stewardship Information Sheet. MSDS available upon request, or on our Web site at [www.COPYLENE.com](http://www.COPYLENE.com). The product specifications are nominal properties and do not reflect normal testing variance and should not be used for specification purposes.

Revision Date May, 2018



Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user's specific application. Phillips 66 Company does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, express or implied, or allegedly arising from any usage of any trade or from any course of dealing in connection with the use of the information contained herein or the product itself. The user expressly assumes all risk and liability, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Further, information contained herein is given without reverence to any intellectual property issues, as well as federal, state or local laws which may be encountered in the use thereof. Such questions should be investigated by the user.