

For more information and technical assistance contact Phillips 66 COPYLENE® Polypropylene at [www.COPYLENE.com](http://www.COPYLENE.com).

## COPYLENE® CR020CL

Polypropylene, Random Copolymer

### Applications:

- Extrusion Blowmolding Processes

### Product Description

- COPYLENE® CR020CL is a random copolymer formulated with advanced clarifier technology and with antistat and is specially designed to excel in extrusion blowmolding processes. EBM bottles will have exceptional gloss and low haze. It is made with a non-phthalate catalyst.

### Product Properties

| Typical Properties  | Method      | Value Unit              |
|---|-------------|-------------------------|
| <b>Physical</b>   |             |                         |
| Melt Flow Rate (230°C/2.16kg)   | ASTM D 1238 | 2.0 g/10 min            |
| Density – Specific Gravity  | ASTM D 792  | 0.902 sp. gr            |
| <b>Mechanical</b>   |             |                         |
| Tensile Strength @ Yield<br>(2 in/min)<br>(50 mm/min)   | ASTM D 638  | 4,000 psi<br>27.5 MPa.  |
| Flexural Modulus<br>(0.05 in/min, 1% Secant, Procedure A)<br>(1 mm/min, 1% Secant, Procedure A) | ASTM D 790  | 140,000 psi<br>965 MPa. |
| Tensile Elongation @Yld   | ASTM D 638  | 14%                     |
| <b>Impact</b>   |             |                         |
| Notched izod impact<br>(73 °F, Method A)<br>(23 °C, Method A)                                   | ASTM D 256  | 5.5 ft-lb/in<br>292 J/m |
| <b>Thermal</b>  |             |                         |
| DTUL @66psi – Unannealed  | ASTM D 648  | 70 °C                   |

For regulatory compliance information, see COPYLENE® CR020CL Product Stewardship Information Sheet. MSDS available upon request, or on our Web site at [www.COPYLENE.com](http://www.COPYLENE.com). The product specifications are nominal properties and do not reflect normal testing variance and should not be used for specification purposes.

Revision Date Feb. 2019



Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user's specific application. Phillips 66 Company does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, express or implied, or allegedly arising from any usage of any trade or from any course of dealing in connection with the use of the information contained herein or the product itself. The user expressly assumes all risk and liability, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Further, information contained herein is given without reverence to any intellectual property issues, as well as federal, state or local laws which may be encountered in the use thereof. Such questions should be investigated by the user.

PHILLIPS 66®, PHILLIPS 66® Shield, COPYLENE® and other trademarks displayed herein are registered trademarks of Phillips 66 Company or one of its subsidiaries.